

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 236 776 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
04.09.2002 Bulletin 2002/36

(51) Int Cl.7: **C09D 7/00, C09D 17/00**

(21) Application number: **02251052.3**

(22) Date of filing: **15.02.2002**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **28.02.2001 US 271997 P**
26.12.2001 US 25706

(71) Applicant: **ROHM AND HAAS COMPANY**
Philadelphia, Pennsylvania 19106-2399 (US)

(72) Inventors:
• **Tanzer, Joseph David**
Fort Washington, Pennsylvania 19034 (US)

• **Harris, Jerome Michael**
Penllyn, Pennsylvania 19422 (US)
• **Eichman, Henry Jude**
Havertown, Pennsylvania 19083 (US)
• **Jamasbi, Homayoun**
Lansdale, Pennsylvania 19446 (US)

(74) Representative: **Kent, Venetia Katherine**
Rohm and Haas (UK) Ltd
European Operations Patent Dept.
Lennig House
2 Mason's Avenue
Croydon, CR9 3NB (GB)

(54) **Method of improving viscosity stability upon addition of a colorant component**

(57) A tinting composition containing a colorant component is disclosed. In addition, a method of improving the viscosity stability of a composition upon the addition of a colorant component employing an associative

thickener, a macromolecular compound having a hydrophobic cavity, a dispersing resin and combinations thereof is disclosed.

EP 1 236 776 A1

Description

[0001] This invention relates to a tinting composition and a method of improving the viscosity stability of a coating composition upon the addition of a colorant component.

[0002] Associative thickeners are water-soluble or water-swellaable polymers that have chemically attached hydrophobic groups. The associative thickeners operate to thicken systems to which they are added by the non-specific associations, such as adsorption on surfaces and aggregation in solution akin to micellization, between the hydrophobic groups on the thickener molecules and moieties on the other components in the system, similar to the non-specific associations of conventional surfactants.

[0003] Since the hydrophobic association exhibited by associative thickeners is non-specific, it is greatly influenced by the presence of surfactants and water miscible organic solvents. The hydrophobes of surfactants may compete for adsorption sites on particle surfaces, and can hinder or enhance associations between thickener hydrophobes, depending on the surfactant HLB. Once an associative thickener is completely desorbed from a particle, such as a latex particle, it can behave like a non-absorbing thickener and flocculate the latex by the volume restriction process.

[0004] A classic problem in paints containing associative thickeners is a drop in mid-shear (Krebs-Stormer) viscosity when colorants that contain high levels of surfactant are added. This is especially problematic when the paint will be tinted to a deep tone because a high level of surfactant generally accompanies the colorant. Colorants are added to paints in units of milliliter of colorant per liter of paint (hereinafter referred to as "ml/liter") or ounces of colorant per gallon of paint (hereinafter referred to as "oz/gal"). Light-tint (pastel) paints typically contain no more than 31.2 ml/liter (4 oz/gal) of colorant. Mid-tone paints typically contain from greater than 31.2ml/liter (4 oz/gal) to 62.5ml/liter (8 oz/gal) of colorant. Deep tone paints typically contain at least 62.6ml/liter (8 oz/gal) of colorant.

[0005] Generally, it is possible to formulate a light tint base at a high enough mid-shear viscosity that colorants added to it will not depress the viscosity to an unacceptable degree. Combinations of associative thickeners have been found to be less sensitive to colorant addition than the individual thickeners alone, in some cases. However, neither of these solutions is completely satisfactory because they either require tedious reformulation, added cost or both, particularly in deep tone paints.

[0006] US-A-5,137,571 and US-A-5,376,709 disclose methods for using cyclodextrin-containing compounds with associative thickeners for a number of uses, including to reduce the viscosity drop of formulations upon the addition of colorants to the formulation. In Example 9 of US-A-5,137,571, β -cyclodextrin, β -cyclodextrin ethoxylate and β -cyclodextrin propoxylate were added to a latex paint formulation containing a hydrophobically-modified ethoxylated urethane resin ("HEUR") to form viscosity-stabilized latex paint formulations. The Krebs-Stormer viscosity of each formulation was measured. Two ounces/gallon of paint of predispersed lampblack colorant were added to the viscosity-stabilized latex paint formulations and the Krebs-Stormer viscosity of each formulation was again measured. The use of post-added cyclodextrin in each case provided a reduction in the viscosity change before and after colorant addition relative to a control system containing no cyclodextrin. The same trend was shown in Example 2 (Table 3.1) of US-A-5,376,709.

[0007] One of the drawbacks of the approach disclosed in US-A-5,137,571 and US-A-5,376,709 is that a single level of cyclodextrin was added to the paint formulation. This does not take into account the type and level of colorant that may be added during the tinting process. As such, if the type and level of cyclodextrin is optimized for one particular colorant, such as lampblack colorant of Example 9 *supra*, then it is unlikely that the type and level of cyclodextrin will be optimized for any other type of colorant. Thus, in some cases too much cyclodextrin may be employed and in some cases too little cyclodextrin may be employed. If the formulation utilizes the maximum level of cyclodextrin to counteract the largest expected viscosity drop (based on colorant type and level), then excess cyclodextrin will be used for most formulations. This is a wasteful and costly approach.

[0008] Many conventional tinting machines employ twelve different colorants to mix the large palette of colors typically offered for most paint lines. Thus, it would be highly desirable to tailor the viscosity stability of any given formulation based on the type and level of colorant component to be added so the proper type and level of cyclodextrin is employed. The composition and method of the present invention provide such a solution.

[0009] The first aspect of this invention provides a tinting composition containing at least one colorant composition and from 0.05 to 15 % dry weight of at least one additive selected from associative thickener and macromolecular compound having a hydrophobic cavity, based on the weight of the at least one colorant composition.

[0010] The second aspect of the present invention provides a method of improving the viscosity stability of a coating composition upon the addition of a colorant component, including the steps of: providing a base paint; and adding to the base paint, a tinting composition containing at least one colorant composition and from 0.05 to 15 % dry weight of at least one additive selected from associative thickener and macromolecular compound having a hydrophobic cavity, based on the weight of the at least one colorant composition.

[0011] As used herein, "universal colorant" shall mean a colorant that is compatible with both water-based and non-aqueous-based compositions.

[0012] As used herein, "compatible" shall mean the mixture of the colorant component and base do not evidence signs of colloidal instability such as flocculation. Preferably, the mixture exhibits less than 5 g of residue such as gel and grit per liter of the composition when the composition is passed through a 200 mesh screen, more preferably less than 1 g of residue.

[0013] As used herein, pigment volume concentration (referred to herein as "PVC") is a measure of how "binder-rich" a formulation is. It is calculated herein by the following formula:

$$\text{PVC} = 100\% \times \frac{(\text{volume of pigment(s)} + \text{volume of extender(s)})}{(\text{volume of pigment(s)} + \text{volume of extender(s)} + \text{volume of binder(s)})}$$

[0014] As used herein, volume solids content ("VS" herein) is the dry volume of pigment(s) plus the dry volume of extender(s) plus the dry volume of binder(s). It is calculated herein by the following formula:

$$\text{VS } 100\% \times \frac{(\text{dry volume of pigment(s)} + \text{dry volume of extender(s)} + \text{dry volume of binder(s)})}{(\text{total volume of formulation})}$$

If additives are present, their volumes are not included in determining the total dry volume.

[0015] As used herein, "KU" shall mean Krebs unit and is a measure of the mid-shear viscosity as measured by a Krebs-Stormer viscometer.

[0016] As used herein, "viscosity stability" shall mean the ability of a composition to resist change in viscosity as measured by KU upon the addition of surfactant or a composition containing surfactant. A preferred viscosity stabilizer for latex paints must provide KU viscosity changes of less than about 10 units upon the addition of up to 93.7ml/liter (12 oz/gal) of colorant. A more preferred viscosity stabilizer for latex paints must provide KU viscosity changes of less than about 5 units upon the addition of up to 93.7ml/liter (12 oz/gal) of colorant.

[0017] The present invention relates to a tinting composition useful for preparing a coating composition with improved viscosity stability. The tinting composition contains at least one colorant composition and at least one additive. The tinting composition may be employed as an universal colorant.

[0018] The colorant composition is a material or mixture of materials added to a composition to impart color to another substance or mixture of materials (herein, to the "base paint") and includes pigments, metal effect agents, and combinations thereof. Examples of suitable pigments include titanium dioxide white, carbon black, lamp black, black iron oxide, red iron oxide, yellow iron oxide, brown iron oxide (a blend of red and yellow oxide with black), phthalocyanine green, phthalocyanine blue, organic red pigment (such as naphthol red, quinacridone red and toulidine red), quinacridone magenta, quinacridone violet, DNA orange, and organic yellow pigment (such as Hansa yellow) and combinations thereof. An examples of a metal effect agent includes mica having a titanium dioxide layer.

[0019] The colorant composition includes surfactants and optionally dispersants to aid in the dispersion and the stabilization of the pigments or the metal effect agents in the liquid medium of the colorant composition. The liquid medium may contain water, glycols such as ethylene glycol and propylene glycol, and alcohols such as isopropanol. Other materials commonly included in colorant compositions are dispersing resins; polyethylene oxide polymers; polyethylene oxide glycols; extenders such as talc and calcium carbonate; humectants; thickeners; defoamer; dispersing resin; and biocides.

[0020] The tinting composition may contain more than one colorant composition. For example, a tinting composition having a brown hue may be prepared by combining a red colorant composition and a yellow colorant composition.

[0021] The tinting composition of the present invention also contains at least one additive to compensate for the viscosity decrease which occurs upon the addition of the colorant composition to a base paint. The additive is an associative thickener or a macromolecular compound having a hydrophobic cavity. The tinting composition may contain one or more associative thickeners, one or more macromolecular compounds having a hydrophobic cavity, or a combination thereof. The level and the type of the associative thickener, and the level and the type of the macromolecular compound having a hydrophobic cavity is chosen to provide a tinting composition that reduces the viscosity decrease upon addition to a base paint. Factors affecting the choice of the associative thickener are the hydrophobe level, the hydrophobe type, and the molecular weight of the associative thickener. Further, it is desirable that the tinting composition has a viscosity which allows easy handling and permits facile mixing into a base paint.

[0022] The associative thickener is a water-soluble or water-swellaable polymer that has chemically attached hydrophobic groups. Examples of associative thickeners include nonionic hydrophobically modified ethylene oxide urethane block copolymers (referred to herein as "HEUR"), hydrophobically modified alkali soluble polymers including hydrophobically modified alkali soluble emulsions (referred to herein as "HASE"), hydrophobically-modified celulosics, including hydrophobically-modified hydroxyethyl cellulose (referred to herein as "HMEC"), hydrophobically modified poly(acrylamide), and mixtures thereof. The tinting composition may contain 0.05 to 15 % dry weight, preferably from 0.1 to 12 % dry weight, and more preferably, from 0.2 to 10 % dry weight of the one or more associative thickeners,

based on the total weight of the colorant composition.

[0023] The macromolecular organic compound having a hydrophobic cavity is a compound which may complex with surfactant to diminish the viscosity lowering effect of the surfactant on the coating composition. Examples of macromolecular organic compounds having a hydrophobic cavity include cyclodextrin, cyclodextrin derivatives, cycloinulohexose, cycloinuloseptose, cycloinulocotose, calyxarene, and cavitand. Cyclodextrin includes α -cyclodextrin, β -cyclodextrin, and γ -cyclodextrin. Cyclodextrin derivatives refers to α -cyclodextrins, β -cyclodextrins, and γ -cyclodextrins in which at least one hydroxyl group located on the rim of the cyclodextrin ring have been functionalized with a substituent group such as methyl, acetyl, hydroxypropyl, and hydroxyethyl groups. Cyclodextrin derivatives also include cyclodextrin molecules with multiple substituent groups including cyclodextrin molecules with more than one type of substituent group. Cyclodextrin derivatives do not include polymers with more than one attached cyclodextrin ring. Preferred cyclodextrin derivatives are methyl- β -cyclodextrin and hydroxypropyl- β -cyclodextrin. Methyl- β -cyclodextrin is the most preferred cyclodextrin derivative.

[0024] The cyclic oligosaccharides having a hydrophobic cavity, such as cycloinulohexose, cycloinuloseptose, useful in the composition and method of the invention are described by Takai *et al.*, *Journal of Organic Chemistry*, 1994, volume 59, number 11, pages 2967-2975.

[0025] The calyxarenes useful in the composition and method of the invention are described in US-A-4,699,966, WO 89/08092; JP-A- 88/197544 and JP-A-89/007837.

[0026] The cavitands useful in the composition and method of the invention are described in Italian application 22522 A/89 and Moran *et al.*, *Journal of the American Chemical Society*, volume 184, 1982, pages 5826-5828.

[0027] The non-cyclic polysaccharides useful in the composition and method of the invention are described in PCT application WO 98/24821. Suitable non-cyclical polysaccharides include both unmodified polysaccharides and modified polysaccharides which are partially or totally derivatized on the hydroxyl groups.

[0028] The tinting composition may contain 0.05 to 15 % dry weight, preferably from 0.1 to 12 % dry weight, and more preferably, from 0.2 to 10 % dry weight of the one or more macromolecular organic compounds having a hydrophobic cavity, based on the total weight of the colorant composition.

[0029] Dispersing resins such as styrenated acrylates may be added to the tinting composition in aid in the dispersion or stability of the pigments and metal effecting agents.

[0030] In one embodiment, the tinting composition contains at least one associative thickener and at least one macromolecular compound having a hydrophobic cavity. The total level of the associative thickener and the macromolecular compound having a hydrophobic cavity is in the range of 0.05 to 15 % dry weight, preferably from 0.1 to 12 % dry weight, and more preferably, from 0.2 to 10 % dry weight, based on the total weight of the colorant composition. In a preferred embodiment, the ratio of the associative thickener and the macromolecular compound having a hydrophobic cavity is in the range of 4:1 to 1:4, preferably in the range of 3:1 to 1:3, and more preferably in the range of 2:1 to 1:2, based on the dry weights of the associative thickener and the macromolecular compound having a hydrophobic cavity.

[0031] In one embodiment, the tinting composition contains at least one associative thickener and at least one macromolecular compound having a hydrophobic cavity. In this embodiment, the ratio of these two additives is such that the moles of the macromolecular compound having a hydrophobic cavity compared to the moles of hydrophobe groups of the associative thickeners is in the range of 1:1 to 1.1:1.

[0032] The tinting composition of this invention may be added to a base paint to prepare the coating composition. The tinting composition is added to change the color of the base paint, or to modify the color or the appearance of a coating prepared from the coating composition. The base paint may be a nonaqueous base paint or an aqueous base paint. Further, the base paint may be a neutral base paint useful for preparing clear coatings or a white base paint. The neutral base paint does not contain titanium dioxide or other materials which provide opacity. The white base paint typically contains titanium dioxide or another white pigments and is used to prepare opaque coatings.

[0033] The titanium dioxide is contained in the white base paint as particles. The titanium dioxide particles typically have an average diameter in the range of 80 nm to 250 nm and may have a coating of silica or a coating of alumina. Suitable forms of titanium dioxide include rutile titanium dioxide and anatase titanium dioxide. The white base paint may contain titanium dioxide at a level of 58 g/liter to 2034 g/liter (10 lbs/100 gal to 350 lbs/100gal of aqueous base paint).

[0034] The nonaqueous base paint contains polymer binder such as acrylic copolymers, polyurethane polymers, polysulphide polymers, and alkyds; and solvents such as toluene, alcohols, and ketones.

[0035] The aqueous base paint contains polymer binder and rheology modifier. The polymer binder is dispersed as polymer particles in the aqueous medium of the aqueous base paint and may have average particle diameters in the range of 20 nm to 1000 nm. Suitable polymer binders include acrylic (co)polymers, vinyl acetate polymers, vinyl/acrylic copolymers, styrene/acrylic copolymers, polyurethanes, polyureas, polyepoxides, polyvinyl chlorides, ethylene/vinyl acetate copolymers, styrene/butadiene copolymers polyester polymer, polyethers and the like, and mixtures thereof. The polymer binder may be provided as an aqueous dispersion such as an emulsion polymer. The polymer binder may be chosen to provide a coating, which is prepared from the aqueous coating composition, with properties such as adhesion to a substrate, gloss, abrasion resistance, and barrier properties such as moisture resistance and solvent

resistance. The level of binder in the aqueous base paint may be in the range of 145 g/liter to 2034 g/liter (25 dry lbs/100 gal to 350 dry lbs/100 gal) of the aqueous base paint.

[0036] The aqueous base paint also contains at least one rheology modifier to thicken the aqueous base paint and to modify the rheology to allow application on substrates without excessive splattering or dripping of the aqueous coating composition, or sag of the wet paint film. Typically more than one rheology modifier is added to a paint to provide an aqueous paint with the desired rheology. Suitable rheology modifiers include nonhydrophobically modified rheology modifiers such as hydroxyethyl cellulose (HEC), alkali soluble emulsions (ASE), and polyvinyl alcohol; and hydrophobically modified rheology modifiers, also referred to as associative thickeners, such as hydrophobically modified ethylene oxide urethane block copolymers (referred to herein as "HEUR"), hydrophobically modified alkali soluble polymers including hydrophobically modified alkali soluble emulsions (referred to herein as "HASE", hydrophobically-modified celulosics, including hydrophobically-modified hydroxyethyl cellulose (referred to herein as "HMHEC"), hydrophobically modified poly(acrylamide); and mixtures thereof. The rheology modifier may be present at a level of 5.8 g/liter to 116 g/liter (1 lb/100 gal to 20 lb/100 gal) of the aqueous base paint.

[0037] As used herein, a "volatile organic compound" (VOC) is defined herein as a carbon containing compound that has a boiling point below 280°C at atmospheric pressure, compounds such as water and ammonia being excluded from VOCs. A volatile organic compound (VOC) may be added to a coating composition to improve the film properties or to aid in the application properties of the coating composition. Examples of such compounds include solvents and coalescents such as glycol ethers, organic esters, aromatic compounds, ethylene and propylene glycol, and aliphatic hydrocarbons.

[0038] In one embodiment, the aqueous base paint is a low VOC composition containing from 0 to less than 6% VOC by weight, preferably from 0 to less than 3% VOC, and more preferably from 0 to less than 2% VOC, based on the total weight of the aqueous base paint. An aqueous coating composition containing from 0 to less than 6% VOC by weight, preferably from 0 to less than 3% VOC, and more preferably from 0 to less than 2% VOC, based on the total weight of the aqueous coating composition, may be prepared from an aqueous base paint having a low VOC composition.

[0039] In one embodiment, the base paint contains at least one associative thickener. The associative thickener may be present in the aqueous composition at a level of at least 0.05% by weight of solids, based on the weight of the composition.

[0040] The method of this invention includes the step of adding the tinting composition of this invention to a base paint to prepare a coating composition. This step is easily achieved by the addition of the tinting composition with mixing.

[0041] The composition and method of the invention are useful for improving the viscosity stability of a composition, particularly upon the addition of a colorant component containing high levels of surfactant. The composition and method of the invention are not limited by the type of colorant component that is added to the composition and are useful for any colorant component that contains surfactant or other additives that may interfere with the non-specific associations of the associative thickeners added to the composition.

[0042] The method of this invention includes the step of adding the tinting composition of this invention to a base paint to prepare the coating composition. This step is easily achieved by the addition of the tinting composition with mixing. The amount of tinting composition added to the base paint may be in the range of 7.8ml/liter (1 oz/gal) to 31.2ml/liter (4 oz/gal) to prepare a light-tint coating composition, from 31.2ml/liter (4 oz/gal) to 62.5ml/liter (8 oz/gal) to prepare a mid-tone coating composition, and from 62.5ml/liter (8 oz/gal) to 93.7ml/liter (12 oz/gal) to prepare a deep tone coating composition.

[0043] The tinting composition and the method of this invention are useful for improving the viscosity stability of a coating composition, particularly upon the addition of the tinting composition to a base paint containing at least one associative thickener. The composition and method of the invention are not limited by the type of pigment that is added to the coating composition.

[0044] The water-resistance properties, including blister resistance, wet adhesion, and scrub resistance of the compositions prepared using the tinting composition and method of this invention, are expected to be improved because of the low molecular weight materials such as surfactants may be complexed with the macromolecular compounds having a hydrophobic cavity. Further, coating compositions prepared using the tinting compositions and the method of this invention, may react more predictably to added tinting compositions, making color matching easier and facilitating the use of software for color matching. Also, viscosity fluctuation in the coating composition is expected to be reduced. Further, the freeze-thaw stability of the coating composition, the dispensing of the tinting composition (no clogs) and the sag resistance properties of wet films prepared from coating compositions using the tinting compositions and method of the invention are expected to be improved.

[0045] The coating composition may be free of organic solvent or it may contain a coalescing solvent. The coating composition may contain typical coating additives such as fillers, defoamers, cross-linkers, catalysts, surfactants, stabilizers, anti-flocculants, coalescents, waxes, antioxidants, and suitable solvents, such as water miscible solvents.

[0046] The coating composition of this invention may be applied by methods well known in the art such as air-assisted

spray, airless spray, plural component spray, brush, roller squeegee, roll coater, curtain coater, and the like. Substrates to which the coating composition may be applied include, for example, timber including but not limited to cedar, pine, teak, oak, maple, and walnut; processed timber including but not limited to medium density fiber board, chip board, laminates; mineral substrates including but not limited to masonry, concrete, stucco, fiber, mortar, cement, cement asbestos, plaster, plasterboard, glazed and unglazed ceramic; metal including but not limited to galvanized iron, galvanized steel, cold rolled steel, aluminum, wrought iron, drop forged steel, and stainless steel; previously painted or primed surfaces (fresh, aged, or weathered) including but not limited to acrylic coatings, vinyl acrylic coatings, styrene acrylic coatings, powder coated surfaces, solvent acrylic coatings, alkyd resin coatings, solvent urethane coatings, and epoxy coatings; synthetic substrates including but not limited to polyvinyl chloride, polyvinylidene chloride, polyethylene, and polypropylene; asphalt; cellulosic substrates such as paper, paperboard, wallpaper, and wallboard; glass; and leather. The coating composition may be used, for example, as a wood coating, maintenance coating, interior or exterior wall coating, metal primer or coating, plastics coating, traffic paint, leather coating, coil coating, architectural coating. Coatings prepared from the coating composition may be flat coatings, satin coatings, semi-gloss coatings, gloss coatings, primer, textured coatings and the like.

[0047] The tinting composition and method of the present invention are particularly useful in systems employing delayed product differentiation, including tinting and mixing of the product components at the point-of-manufacture, point-of-sale or point-of-use, such as those disclosed in U.S. Provisional Applications Serial Nos. 60/183,655 filed February 18, 2000, 60/183,656 filed February 18, 2000, and 60/247,639 filed November 10, 2000.

[0048] All ranges used herein are inclusive and combinable. Some embodiments of the present invention will now be described in detail in the following

Examples.

[0049] The Krebs-Stormer viscosity was measured using ASTM method D562.

Example 1 - Preparation of Base Paint Containing HEUR Associative Thickener

[0050] A base paint was prepared containing associative thickeners. The associative thickeners were hydrophobically modified ethylene oxide urethane block copolymers. First, a paint grind was prepared by combining the materials in the order listed in Table 1.1.

Table 1.1 -

Paint Grind	
Material	Amount
propylene glycol	34.56 g
Water	25.04 g
Tamol™ 731 dispersant	6.89 g
clay	70.00 g
Foamaster™ PL defoamer	0.89 g
Nurosept 95 biocide	0.07 g
Tamol is a trademark of Rohm and Haas Company. Foamaster is a trademark of Cognis Corp. Nurosept is a trademark of the Huls America Corp.	

[0051] Next, a base paint was prepared by combining the paint grind with the materials listed in Table 1.2.

Table 1.2 -

Base Paint Containing HEUR Associative Thickener	
Material	Amount
Water	150.25 g

Table 1.2 - (continued)

Base Paint Containing HEUR Associative Thickener	
Material	Amount
Acrysol™ SCT-275 rheology modifier (HEUR)	26.00 g
ammonia (28%)	2.00 g
Triton™ X-100 surfactant	4.45 g
Texanol™ coalescent	15.80 g
propylene glycol	8.64 g
polyvinyl acetate polymer binder	472.50 g
propylene glycol	8.64 g
polyvinyl acetate polymer binder	472.50 g
Acrysol is a trademark of Rohm and Haas Company. Triton is a trademark of Dow Chemical Co. Texanol is a trademark of Eastman Chemical Co. Isopar is a trademark of Exxon Corp.	

[0052] The base paint is an aqueous base paint containing a HEUR associative thickener and had a pH of 8.4, a PVC of 10.5% and a VS of 30%.

Example 2 - Preparation of Base Paint Containing HASE Associative Thickener

[0053] A base paint was prepared containing an associative thickener. The associative thickener was a hydrophobically modified alkali soluble emulsion. First, a paint grind was prepared by according to the procedure in Table 1.1. Next, a base paint was prepared according to the procedure in Table 1.2 except that 14.00 g of Acrysol™ DR-73 rheology modifier (HASE) was substituted for the Acrysol™ SCT-275 rheology modifier.

[0054] The base paint was an aqueous base paint containing a HASE associative thickener and had a pH of 8.5, a PVC of 10.5%, and a VS of 30%.

Example 3 - Coating Composition Containing Tinting Composition Containing Associative Thickener and Macromolecular Compound Having a Hydrophobic Cavity

[0055] An additive mixture was prepared by combining 2 parts by dry weight of Acrysol™ RM-8 rheology modifier (Rohm and Haas Company), an HEUR associative thickener, and 1 part by dry weight of methyl-β-cyclodextrin. The additive mixture was added to several colorant compositions at levels of 5, 10 and 15 dry weight % with mixing to prepare the tinting compositions.

[0056] The coating compositions were prepared by mixing the tinting compositions into the base paints of Example 1 and Example 2 at a level of 93.7 ml/liter (12oz/gal). The Krebs-Stormer viscosity of the coating compositions were measured prior to and 24 hours after the addition of the tinting compositions.

Table 3.1 -

Viscosity Decrease (KU) for Coating Composition Containing HEUR Rheology Modifier and Tinting Composition				
% Additive Mixture in Tinting Composition	White	Blue	Yellow	Black
0	-11	-28	-18	-32
5	1	-23	-7	-25
10	8	-15	-1	-18
15	15	10	7	-11

Table 3.2 -

Viscosity Decrease (KU) for Coating Composition Containing HASE Rheology Modifier and Tinting Composition				
% Additive Mixture in Tinting Composition	White	Blue	Yellow	Black
0	-2	-12	-6	-10
5	12	-6	12	-5
10	23	-1	14	3
15	34	7	23	13

[0057] The results in Table 3.1 and Table 3.2 show that the tinting compositions containing the combination of associative thickener and macromolecular compound having a hydrophobic cavity as additives provided coating compositions with smaller viscosity decreases compared the colorant composition which did not contain an additive.

Example 4 - Coating Composition Containing Tinting Composition Containing Associative Thickener

[0058] A base paint was prepared containing associative thickeners. The associative thickeners were hydrophobically modified ethylene oxide urethane block copolymers. First, a titanium dioxide grind was prepared by combining the materials in the order listed in Table 4.1.

Table 4.1 -

Titanium Dioxide Grind	
Material	Amount
Water	53.11 g
propylene glycol	1.70 g
Tamol™ 731 dispersant	1.00 g
Triton™ CR-10 surfactant	0.07 g
Foamaster™ VL defoamer	0.10 g
Kathon™ LX (1.5%)	0.07 g
Rhoplex™ SG-10M polymer binder	200.00 g
Ti-Pure™ R-706 titanium dioxide	25.00 g
Acrysol™ RM-2020 NPR rheology modifier	10.00 g
Water	50.00 g
Kathon, Rhoplex, and Acrysol are trademarks of Rohm and Haas Company.	
Foamaster is a trademark of Cognis Corp.	
Ti-Pure is a trademark of E.I. DuPont de Nemours and Co.	

[0059] Next, a base paint was prepared by combining the titanium dioxide grind with the materials listed in Table 4.2.

Table 4.2 -

Aqueous Base Paint Formulation	
Material	Amount
Water	62.78 g
Rhoplex™ SG-10M polymer binder	403.13 g
Ropaque™ Ultra plastic pigment	5.60 g
Texanol™ coalescent	30.33 g

Table 4.2 - (continued)

Aqueous Base Paint Formulation	
Material	Amount
ammonia (28%)	1.43 g
Acrysol™ RM-2020 NPR rheology modifier	14.24 g
Acrysol™ RM-825 rheology modifier	0.65 g
Foamaster™ VL defoamer	2.00 g
water	25.00 g
Ropaque is a trademark of Rohm and Haas Company.	
Texanol is a trademark of Eastman Chemical Co.	

[0060] The base paint was an aqueous base paint containing HEUR associative thickeners and had a PVC of 3.3% and a VS of 33.8%.

[0061] A phthalo blue colorant composition (100g) was formulated with 10.5 g of Acrysol™ RM-825 rheology modifier (25% active) and 6g water to prepare the tinting composition. The Acrysol™ RM-825 rheology modifier is a HEUR associative thickener. The coating composition, Example 4.1, was prepared by admixing 20.51g of the tinting composition into 100g of the base paint. A comparative coating composition, Comparative A, was prepared by adding 100 g of the phthalo blue colorant composition and 16.5g water to the base paint.

Table 4.3 -

Viscosity Decrease (KU) for Coating Composition Containing HEUR Rheology Modifier and Tinting Composition Containing Associative Thickener	
Coating Composition	Viscosity Change (KU)
Example 4.1	-15
Comparative A	-27

The results in Table 4.3 show that the tinting composition of this invention, which contains an associative thickener, provided a coating composition with a smaller decrease in viscosity compared to the comparative coating composition containing the colorant composition.

Example 5 - Coating Composition Containing Tinting Composition Containing Macromolecular Compound Having a Hydrophobic Cavity

[0062] The base paint was an aqueous base paint containing HEUR associative thickeners, prepared in Example 4.

[0063] A phthalo blue colorant composition (100g) was formulated with 0.85 g methyl- β -cyclodextrin (50% active) and 15.65g water to prepare the tinting composition. The coating composition, Example 5.1, was prepared by admixing 20.51g of the tinting composition into 100g of the base paint. A comparative coating composition was Comparative A of Example 4.

Table 5.1 -

Viscosity Decrease (KU) for Coating Composition Containing HEUR Rheology Modifier and Tinting Composition Containing Macromolecular Compound Having a Hydrophobic Cavity	
Coating Composition	Viscosity Change (KU)
Example 5.1	-23
Comparative A	-27

The results in Table 5.1 show that the tinting composition of this invention, which contains a macromolecular compound having a hydrophobic cavity, provided a coating composition with a smaller decrease in viscosity compared to the comparative coating composition containing the colorant composition.

Claims

1. A tinting composition comprising:

- a) at least one colorant composition; and
- b) from 0.05 to 15 % dry weight of at least one additive selected from the group consisting of associative thickener and macromolecular compound having a hydrophobic cavity, based on the weight of said at least one colorant composition.

2. The tinting composition according to claim 1 comprising from 0.05 to 15 % dry weight of said one macromolecular compound having a hydrophobic cavity.

3. The tinting composition according to claim 1 comprising from 0.05 to 15 % dry weight of said associative thickener.

4. The tinting composition according to claim 1, wherein the ratio of said macromolecular compound having a hydrophobic cavity to said associative thickener is in the range of 4:1 to 1:4, based on dry weights.

5. The tinting composition according to claim 1, 2, 3, or 4 wherein said associative thickener is selected from the group consisting of nonionic hydrophobically modified ethylene oxide urethane block copolymer, hydrophobically modified alkali soluble polymer, hydrophobically-modified cellulosic, hydrophobically-modified polyacrylamide, and mixtures thereof.

6. A method of improving the viscosity stability of a coating composition upon the addition of a colorant component, comprising the steps of:

- a) providing a base paint; and
- b) adding to said base paint, a tinting composition comprising:

- i) at least one colorant composition; and
- ii) from 0.05 to 15 % dry weight of at least one additive selected from the group consisting of associative thickener and macromolecular compound having a hydrophobic cavity, based on the weight of said at least one colorant composition.

7. The method of claim 6 wherein said tinting composition comprising from 0.05 to 15 % dry weight of said macromolecular compound having a hydrophobic cavity.

8. The method of claim 6 wherein said tinting composition comprising from 0.05 to 15 % dry weight of said associative thickener.

9. The method of claim 6 wherein said tinting composition has a ratio of said macromolecular compound having a hydrophobic cavity to said associative thickener is in the range of 4:1 to 1:4, based on dry weights.

10. The method according to claim 6, 7, 8, or 9 wherein said base paint comprises at least one associative thickener selected from the group consisting of nonionic hydrophobically modified ethylene oxide urethane block copolymer, hydrophobically modified alkali soluble polymer, hydrophobically-modified cellulosic, hydrophobically-modified polyacrylamide, and mixtures thereof.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 25 1052

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	WO 93 09187 A (DU PONT) 13 May 1993 (1993-05-13) * claims 1-19 *	1-10	C09D7/00 C09D17/00
A	EP 0 747 456 A (ROHM & HAAS) 11 December 1996 (1996-12-11) * page 7, line 53 - page 8, line 25 *	6	
A	EP 0 867 481 A (HERCULES INC) 30 September 1998 (1998-09-30) * claims 1-20 *	1	
A	EP 0 614 950 A (ROHM & HAAS) 14 September 1994 (1994-09-14)		
A,D	& US 5 376 709 A (ROHM AND HAAS COMPANY) 11 August 1992 (1992-08-11)		
A	EP 0 460 896 A (ROHM & HAAS) 11 December 1991 (1991-12-11)		
A,D	& US 5 137 571 A (ROHM AND HAAS COMPANY) 27 December 1994 (1994-12-27)		
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C09D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 28 May 2002	Examiner Miller, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (P04/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 25 1052

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

28-05-2002

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
WO 9309187	A	13-05-1993	AU	2930992 A	07-06-1993
			WO	9309187 A1	13-05-1993
EP 0747456	A	11-12-1996	US	5962580 A	05-10-1999
			AU	714891 B2	13-01-2000
			AU	5246896 A	19-12-1996
			BR	9602621 A	22-04-1998
			CA	2177547 A1	08-12-1996
			CN	1140736 A	22-01-1997
			EP	0747456 A2	11-12-1996
			JP	9003363 A	07-01-1997
			TW	448220 B	01-08-2001
EP 0867481	A	30-09-1998	EP	0867481 A1	30-09-1998
			AU	738968 B2	04-10-2001
			AU	5970098 A	01-10-1998
			BR	9801137 A	05-10-1999
			CA	2233145 A1	27-09-1998
			CN	1195008 A	07-10-1998
			JP	11029721 A	02-02-1999
			NZ	330024 A	29-07-1999
			TR	9800558 A1	21-10-1998
			US	5922119 A	13-07-1999
			ZA	9802617 A	28-09-1998
EP 0614950	A	14-09-1994	US	5376709 A	27-12-1994
			AT	145418 T	15-12-1996
			AU	663245 B2	28-09-1995
			AU	5649094 A	15-09-1994
			BR	9401128 A	07-03-1995
			CA	2116927 A1	13-09-1994
			CN	1095731 A ,B	30-11-1994
			DE	69400928 D1	02-01-1997
			DE	69400928 T2	07-05-1997
			DK	614950 T3	09-12-1996
			EP	0614950 A1	14-09-1994
			ES	2095128 T3	01-02-1997
			FI	941185 A	13-09-1994
			GR	3021749 T3	28-02-1997
			HK	122297 A	12-09-1997
			IL	108802 A	30-10-1998
			JP	7003241 A	06-01-1995
			NO	940782 A	13-09-1994
			NZ	260009 A	26-05-1995
			PH	30128 A	27-12-1996
			RU	2132344 C1	27-06-1999

EPC FORM RULES

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 25 1052

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

28-05-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0614950	A		SG 67893 A1	19-10-1999
			ZA 9401665 A	13-09-1994
EP 0460896	A	11-12-1991	US 5137571 A	11-08-1992
			AT 126817 T	15-09-1995
			AU 652937 B2	15-09-1994
			AU 7812891 A	12-12-1991
			BR 9102314 A	14-01-1992
			CA 2043342 A1	06-12-1991
			CN 1057064 A ,B	18-12-1991
			DE 69112285 D1	28-09-1995
			DE 69112285 T2	21-03-1996
			DK 460896 T3	25-09-1995
			EP 0460896 A2	11-12-1991
			ES 2077801 T3	01-12-1995
			FI 912689 A	06-12-1991
			HK 25896 A	16-02-1996
			IE 911903 A1	18-12-1991
			JP 3055816 B2	26-06-2000
			JP 4227986 A	18-08-1992
			JP 2000178530 A	27-06-2000
			JP 3173603 B2	04-06-2001
			JP 2000178507 A	27-06-2000
			KR 171603 B1	20-03-1999
			NO 300424 B1	26-05-1997
			NZ 238387 A	26-10-1993
			PT 97871 A	30-04-1992